

iNDUO[®] 100C-T5 BARI

FOR ALL FABRICS

OPTION

CERTIFICATIONS

OEKO-TEX[®]
CONFIDENCE IN TEXTILES
STANDARD 100



CHARACTERISTICS	SPECIFICATIONS	NORMS
COMPOSITION	100% COTTON	ISO 1833
WEAVE	CROSSED 2X2	ISO 7211-1
THREAD COUNT (NE)	WARP 80/2 WEFT 80/2	ISO 7211-5
TOTAL / USABLE WIDTH (CM/CM) (+/- 1CM)	146 / 143	ISO 5025
MINIMUM NUMBER OF THREADS PER CM	WARP 50 WEFT 35	ISO 7211-2
SURFACE MASS (G/M ²) (G/ML) (+/- 3%)	126 / 184	ISO 3801
SERVICING		ISO 3758:2012

PROPERTIES	SPECIFICATIONS	NORMS
PH	6-8	ISO 3071
TENSILE STRENGTH (N)	WARP >400 WEFT >200	ISO 13934-2
SLIDIND SEAM (MM)	WARP <1MM WEFT <1MM	ISO 13936-2
GUARANTEED MARTINDALE ABRASION RESISTANCE (NO. OF TURNS)	30 000	ISO 12947-2
MINIMUM NOTE PILLING + TRIMMING (BOX -NOTE 1-5)	5	ISO 12945-1
WASHING STABILITY (%)	WARP <3 WEFT <3	ISO 5077
DRYING RATE (%/MIN)	0.03	ISO 17617
DRYING TIME (MIN)	70	
SPRAY TEST	4/5	ISO 4920
SPRAY TEST AFTER 40 WASHES	4/5	ISO 4920 / ISO 6330

DYEING	SPECIFICATIONS	NORMS
SHADE TYPE	YARN DYED	
COLOUR FASTNESS TO LIGHT	3	ISO 105-B02
C.F. TO WASHING	4,5	ISO 105-C06
C.F. TO RUBBING DRY	4,5	ISO 105-X12
C.F. TO RUBBING WET	4,5	ISO 105-X12